

ARIHANT



BASIC CHROMIUM SULPHATE FOR LEATHER

Basic Chromium Sulphate - **ARIHANT 26**

Self Basifying Basic Chromium Sulphate - **ARIHANT SB**

Salt Free Self Basifying Chrome Tanning Agent - **ARIHANT SF**

SELF BASIFYING BASIC CHROMIUM SULPHATE



ADVANTAGES

- No Need of Basifying Chemicals
- Yield Firm & Compact Collagen Structure Thereby Preventing Belly Emptiness
- More Fullness and Even Grain Leather Resulting in More Cutting Yield
- Leather Will Have Better Physical Properties Compared to Normal Chrome Tanning
- Excellent Grain Tightness & Uniformity
- Economical

SALT FREE SELF BASIFYING CHROME TANNING AGENT



ADVANTAGES

- Total Elimination of Pickling in Leather Processing
- High Chromium Exhaustion
- No need of Chrome Recovery
- Saving in use of Other Chemicals & Process Time
- Low Total Dissolved Solids (TDS)
- Eco Friendly
- Technology Suitable for all Substrates & Leathers

BASIC CHROMIUM SULPHATE



Particulars	Arihant 26	Arihant
Cr_2O_3	$26 \pm 1\%$	$23 \pm 1\%$
Basicity	$33 \pm 2\%$	$33 \pm 2\%$
pH (10% Solution)	$3.0 \pm .2$	$3.0 \pm .2$

ARIHANT INTERMEDIATES (MADRAS) PVT. LTD.



Regd. Off: 1, Maylai Ranganathan Street,
1st Floor, T. Nagar, Chennai - 600 017. India
Phone: +91 96000 28180 / +91 94440 54534

Email: vishal@arihantchrome.com

Website : www.arihantchrome.com

Factory: Sathamai Village, Maduranthakam Taluk,
Kancheepuram Dist. Tamilnadu.